



TECHNICAL DATA

Revised: 01/2008
Replaces: 11/2007

FOAMSEAL[®] F13268/FSA21 EXTRUSION BENDING FOAM

Description

A water blown, two component polyurethane foam system formulated to provide internal cavity support in vinyl bending processing. Extrusions filled with this material can be welded with no deterioration in weld strength, welding plate fouling or off gassing. Profiles filled with the material have lower "U" values. Similar foam systems have been found to exhibit sound transmission loss (STL) properties.

Application Data

Equipment:	Proportioner must be capable of holding the mix ratio at $\pm 2\%$ and metering the materials at required temperatures and pressures. Foam gun must be capable of efficiently mixing the two components and dispensing them in a uniform stream.
Mix Ratio: (by volume)	"2.7" F13268 : "1" FSA 21
Process Temperature:	100° - 110°F
Process Pressure:	800 – 1000 psi

Material Characteristics

Viscosity: @ 72°F		
	FSA21	75 cps
	F13268	1130 cps
Specific Gravity:		
	FSA21	1.23
	F13268	1.06
Density: Free rise		5.0 pcf
"K" Factor:		
	btu in/hr-ft ² -°F	0.263
Cure Time:		48 hrs @ 75°F
Storage Temperature:		
	FSA21	65° - 90°F
	F13268	65° - 90°F

Shelf Life

This product is warranted against manufacturing defects for a period of six months from the date of manufacture.

Safety Information

- Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information.
- Do not apply material in enclosed areas without adequate air exchange and ventilation.
- Wear protective clothing, gloves and eye protection.
- Breathing fumes or contact with the skin may cause severe allergic reactions.
- **This product is intended for industrial use by properly trained professional applicators only.**

Notes

- Extrusion length, cavity size and cavity geometry may affect processing variables such as fill angle, material temperature and material pressure.
- Available in non-returnable 55 gallon steel drums and returnable 250 gallon tote bins.

ITW FUTURA COATINGS, 1685 GALT INDUSTRIAL BLVD., ST LOUIS, MO, (314) 733-1110

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact ITW Futura Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to ITW Futura quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ITW FUTURA, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE

01/2008 F13268/FSA21