



# TECHNICAL DATA

Revised Date: 01/2008  
Replaces Date: 06/2006

## P11662/FSA RIGID FOAM

### Description

A water blown, two component polyurethane closed cell rigid foam system formulated for cavity fill applications. Suitable for hand mix or machine pour.

### Application Data

<b>Mix Ratio:</b> (by volume)	"1" P11662 : "1.3" FSA
<b>Process Temperature:</b>	70° - 90°F

### Material Characteristics

<b>Viscosity:</b> @ 72°F	
FSA	200 cps
P11662	700 – 900 cps
<b>Specific Gravity:</b>	
FSA	1.23
P11662	1.06
<b>Density:</b> Free rise	2.5 – 2.9 pcf
<b>Hand Mix Reactivity @ 72° F</b>	
Cream time	32 – 47 sec
Tack free time	285 – 332 sec
<b>Cure Time:</b>	48 hrs @ 75°F
<b>Storage Temperature:</b>	
FSA	65° - 90°F
P11662	65° - 90°F

### Shelf Life

This product is warranted against manufacturing defects for a period of six months from the date of manufacture.

### Safety Information

- Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information.
- Do not apply material in enclosed areas without adequate air exchange and ventilation.
- Wear protective clothing, gloves and eye protection.
- Breathing fumes or contact with the skin may cause severe allergic reactions.
- **This product is intended for industrial use by properly trained professional applicators only.**

ITW FUTURA COATINGS, 1685 GALT INDUSTRIAL BLVD., ST LOUIS, MO, (314) 733-1110

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact ITW Futura Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to ITW Futura quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ITW FUTURA, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

01/2008 P11662/FSA