



TECHNICAL DATA

Revised Date: 01/2008
Replaces Date: 02/2006

S13209/FSA RIGID SPRAY SYSTEM

Description

A polyurethane rigid spray foam designed for in-plant processing for bus manufacturing. This system features excellent sprayability and adhesion to a variety of substrates

Application Data

Equipment:	Proportioner must be capable of holding the mix ratio at $\pm 2\%$ and metering the materials at required temperatures and pressures. Spray gun must be capable of efficiently mixing the two components and dispensing them in an evenly shaped pattern.
Mix Ratio: (by volume)	5 "FSA" : 4 "S13209"
Process Temperature:	120° - 135°F
Process Pressure:	800 – 1000 psi

Material Characteristics

Viscosity: @ 72°F	
FSA	200 cps
S13209	800 cps
Specific Gravity:	
FSA	1.23
S13209	1.17
Density: sprayed-in-place	2.1 pcf
Substrate Temperature:	55 – 95°F
Flammability: FMVSS 302	Passes
Initial R Value:	6.0
Storage Temperature:	
FSA	65° - 85°F
S13209	65° - 85°F

Shelf Life

This product is warranted against manufacturing defects for a period of six months from the date of manufacture.

Safety Information

- Notes**
- The flammability data is not intended to reflect the hazards presented by this or any other material under actual fire conditions.
 - This material should not be used where construction codes apply.
- Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information.
 - Do not apply material in enclosed areas without adequate air exchange and ventilation.
 - All application personnel must use respirators rated for organic vapors, or in confined spaces wear fresh air respirators or fresh air hoods.
 - Wear protective clothing, gloves and eye protection.
 - Breathing fumes or contact with the skin may cause severe allergic reactions.
 - This product is intended for industrial use by properly trained professional applicators only.**

ITW FUTURA COATINGS, 1685 GALT INDUSTRIAL BLVD., ST LOUIS, MO, (314) 733-1110

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact ITW Futura Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to ITW Futura quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ITW FUTURA, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.