



TECHNICAL DATA

Revised Date: 01/2008
Replaces Date: 04/2007

PROTEC[®] II PW-ER (20090) POTABLE WATER TANK LINING

Product Description

100% solids, direct to metal, fast-set, two component urethane certified per NSF/ANSI Standard 61 for use as a lining in potable water tanks and pipe. It provides a very hard, tough surface with outstanding edge retention, adhesion and impact resistance. Requires plural component, heated application equipment.

Features

- Complies with NSF/ANSI Standard 61
- Excellent adhesion directly to steel
- Excellent edge retention
- Zero VOC.
- No taste or odor concerns caused by entrapped solvents.
- Convenient 1:1 mix ratio.
- Unlimited film build with single multi-pass coats.
- Meets FDA 21CFR 175.300 for food contact.
- Fast curing for increased productivity and short turn around times.

Recommended Uses

As a one or two coat direct to metal lining system for steel potable water tanks and pipes.

Primers

Steel: None

Other: Contact ITW Futura Coatings for recommendations.

Typical Properties

Solids by Volume	100%
Volatile Organic Compounds	0.0 lb/gal (0 g/l)
Theoretical Coverage	1604 ft ² @ 1 mil (3.8 m ² @ 1 mm)
Recommend DFT (Typical)	15 – 50 mils (0.4 – 1.3 mm)
Number of Coats	1 or more
Mix Ratio (by volume)	1”A” : 1”B”
Flash Point (PMCC) <i>Mixed</i>	311°F (168°C)
Shelf Life @ 60-90°F (16-32°C)	Part A 12 months Part B 12 months
Color	White -1120

Specification Data

Elongation – ASTM D 412	< 10%
Adhesion – ASTM D 4541	> 2500 psi
Abrasion Resistance ASTM D 4060 CS 17 wheel, 1000g, 1000 cycles	45 mg loss
Tensile Strength ASTM D 412	4000 psi
Impact Resistance ASTM G 14 – 15 mm ball	125.4 in-lbs (1447 cm/kg)
Hardness – ASTM D 2240	75 Shore “D”
Flexibility 180° Bend over 4” mandrel 90° Bend over 4” mandrel	Pass – 30 mils @ 75°F Pass – 30 mils @ -40°F
Permeability – ASTM E 96 (60 mil dry film thickness)	0.0078 U.S. perms 0.0113 metric perms
Accelerated Weathering ASTM G 23 – Q/UV, 2500 hrs	No cracking, checking or loss of flexibility; slight chalking.
Cathodic Disbondment ASTM G 95 – Average Radius	30 days @ 75°F 7 mm 14 days @ 149°F 8 mm

Ordering Information

Packaging:	10 gal & 110 gal kits
Shipping Weight:	10.5 lb/gal (4.7 kg/gal)

APPLICATION INFORMATION PROTEC II PW-ER

Surface Preparation

Remove all oil, grease or other contaminants from the surface to be coated in accordance with SSPC-SP 1.

Steel:

Immersion and Non-Immersion: Abrasive blast to a Near White Blast in accordance with SSPC-SP 10 and obtain a 3-4 mil (75-100µ) angular anchor pattern.

Other: Contact ITW Futura Coatings for specific recommendations.

Mixing

Power mix "B" component thoroughly for 15 to 20 minutes to a uniform consistency, "A" component does not require mixing.

DO NOT BATCH MIX.

Note: This product will develop phase separation and must be mixed thoroughly prior to use.

Thinning

DO NOT THIN

Pot Life

Material Temperature	Time
75°F (24°C)	< 30 seconds

Application Conditions

	Normal	Minimum	Maximum
Material*	135-150°F (57-65°C)	130°F (54°C)	170°F (77°C)
Surface	75-90°F (24-32°C)	45°F (7°C)	120°F (49°C)
Ambient	75-90°F (24-32°C)	35°F (2°C)	120°F (49°C)
Humidity	30-50%	0%	85%

*Materials must be preheated to 75-90°F (24-32°C) min prior to use. Surface temperature must be 5°F (3°C) above the dew point.

Application Equipment

Heated Plural Component Airless (only)

Applicator training is required and spray equipment must be approved by ITW Futura Coatings Technical Service.

- 1:1 ratio capable of producing a minimum delivery rate of 1¼ gallons per minute at a tip pressure of 2500-3000 psi.
- Proportioner heaters and heated hose capable of maintaining material temperatures of 135-150°F (57-65°C) at the spray tip.
- Drum heaters capable of maintaining material temperatures of 75-90°F (24-32°C) during application
- 2:1 ratio transfer pumps minimum.
- Contact ITW Futura Coatings for specific information..

Clean Up

Use MEK or a 1:1 blend of MEK and Toluol.

Cure Time

These times are based on a 30-50% RH. Excessive film thickness, cooler temperatures or inadequate ventilation will require longer cure times.

Surface Temperature

	50-60°F (10-15°C)	70-80°F (21-27°C)	90-100°F (32-38°C)
Surface dry	4-10 minutes	3-4 minutes	½-2 minutes
Hard Film	10-20 minutes	5-10 minutes	5 minutes
Recoat (min)	4-10 minutes	3-4 minutes	½-2 minutes
Recoat (max)	4 hours	4 hours	4 hours
Full cure	3 days	2 days	24 hours

- If the maximum recoat time has been exceeded contact ITW Futura Coatings for recommended recoat procedure.
- Holiday testing per NACE RP0199-98 can be started once the cure time shown for "Hard Film" has been achieved.

Repair

- Contact ITW Futura Coatings for specific recommendations.

Safety Information

- Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information.
- Do not apply material in enclosed areas without adequate air exchange and ventilation.
- All application personnel must use fresh air respirators or fresh air hoods.
- Wear protective clothing, gloves and eye protection.
- Breathing fumes or contact with the skin may cause severe allergic reactions.
- **This product is intended for industrial use by properly trained professional applicators only.**

Storage Conditions

- Urethane coatings need to be protected from moisture contamination. Store drums and pails in a dry location at 60-90°F (16-32°C).
- Drums must be kept sealed at all times with a positive feed dry air, nitrogen blanket or desiccant cartridge system.
- Materials must be kept above **50°F (10°C)**.

ITW FUTURA COATINGS, 1685 GALT INDUSTRIAL BLVD., ST LOUIS, MO, (314) 733-1110

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact ITW Futura Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to ITW Futura quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ITW FUTURA, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.